



FLOKSER TEKSTIL SAN. Ve TIC A.S.
HADIMKOY MAH. URGUPLU CD. NO : 7
34555 ARNAVUTKOY /ISTANBUL / TURKEY

Product sample: POLIUREA AROMATICA ELASTOMERO

Received: 31.01.2018

Start test: 01.02.2018

End test: 12.02.2018

Test Report: 12.02.2018

Analytical specifications: Regulation "UE 2002/72/CE DELLA COMMISSIONE del 6 agosto 2002" relating to plastic materials and articles intended to come into contact with foodstuffs.

Product Features: No. 01 specimens of size 29.4 cm x 29.4 cm x 0.3 cm.

Test conditions: For overall migration test were employed N°. 03 specimens (test duration: 10 days).

Results of overall migration tests


Sample (POLIUREA AROMATICA ELASTOMERO)	Duration of the test	Test temperature	Test result
No. 03 tests in distilled water (M ¹ /M ² /M ³)	240 h for (M ¹ /M ² /M ³)	40 °C	< 0.01 mg/dm ²

Comment: Based on the tests performed to evaluate the concentration of chemicals overall migration of the product " **POLIUREA AROMATICA ELASTOMERO** ", after contact with the water simulant, is that this product does not assign any component in the normal conditions of use. Therefore, in compliance with current legislation, cited above, the compound is suitable to come into contact with food and can be used in the manufacture of materials intended to come into contact with foodstuffs.

Novi Ligure, 12.02.2018

The Resp. of the Laboratory

Dott.ssa *Moredana Zambelli*



VEDERE CONDIZIONI DI FORNITURA SUL RETRO